

# J-FLEX MATERIAL DATA SHEET

V-SIL<sup>®</sup> SILICONE RUBBER 60° SHORE 'A'  
FINE FABRIC IMPRESSION (No Talc)



PROPERTY	VALUE
QUALITY DESIGNATION	NE160
COLOUR	Red Iron Oxide
HARDNESS	60° SHORE A (+/-5)
TENSILE STRENGTH	7 Mpa
ELONGATION @ BREAK	350%
FULLY POST CURED	5 hours @ 175°C
TEMPERATURE RANGE	-60°C to +230°C Continuous

Other colours made to order

**V-SIL<sup>®</sup>**  
VALUE FOR MONEY  
SILICONE PRODUCTS

V-Sil<sup>®</sup> is a registered trade mark of J-Flex Rubber Products

Issue 1

January 2013



**J-FLEX**

Engineering Rubber Components & Specialised Sheeting Products

Units 1 & 2, London Road Business Park, Retford,  
Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712 400 fax: +44 (0) 1777 712 409

[www.j-flex.co.uk](http://www.j-flex.co.uk)

