

J-FLEX MATERIAL DATA SHEET

WRAS APPROVED 80° (+/-5°) SHORE
PEROXIDE CURED E.P.D.M
MOULDED SHEETS

COMPOUND REF. NO. WRAS 80E

For Hot & Cold Water Up To 85°C

PROPERTY	VALUE
DUROMETER HARDNESS	80° (+/-5°) Shore A
TENSILE STRENGTH	2175 psi-min (15 Mpa)
ULTIMATE ELONGATION	150% - min
COMPRESSION SET (22 hours @ 125°C)	10% max

Tested in accordance with ASTM D2000 M2 CA810 A25 B35

WRAS APPROVAL NO. 1505542 – Meeting the requirements of BS6920- 1: 2000

Issue 5

August 2016



A member of the
Gasket Cutters
Association



Certificate No. RS 27920
Approved to BS EN ISO 9001:2008

J-FLEX RUBBER PRODUCTS
Engineering Rubber Components & Specialised Sheeting Products

Units 1 & 2, London Road Business Park, Retford,
Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712 400 fax: +44 (0) 1777 712 409
www.j-flex.co.uk

