

Product information

ROTEISENOXID SILIKON VERSTÄRKT MIT 1-LAGIGER GLASGEWEBE-EINLAGE

GRUNDGEWEBE: GLASTUCH	WERT
Zusammensetzung Kett- und Schussfäden	Glas
Gewicht	204 g/m ²
Anzahl Kettfäden	680 dtex
Anzahl Schussfäden	680 dtex
Bindung	Leinwandbindung
Dicke	0,18 mm

VERBUNDEIGENSCHAFTEN	WERT
Zusammensetzung	Silikongummi
Farbe	Roteisenoxid
Gewicht	1,20 kg/m ³
Härte	60 °
Adhäsion	>9 N/mm
Temperaturbereich	-60 °C bis +230 °C

Fertigprodukt-Eigenschaften

Spezifikation	Aufbau (Sil + Glas + Sil)	Dicke	Breite
1,5 mm	0,65 + 0,2 + 0,65	1,5 mm (+/-0,2 mm)	1200 mm max.
2,0 mm	0,9 + 0,2 + 0,9	2,0 mm (+/-0,2 mm)	1200 mm max.
3,0 mm	1,4 + 0,2 + 1,4	3,0 mm (+/-0,2 mm)	1200 mm max.
4,0 mm	1,9 + 0,2 + 1,9	4,0 mm (+/-0,2 mm)	1200 mm max.

Ausgabe 4

March 2011

Check out the download area of our website
www.j-flex.co.uk for other product information



Clockpress Limited
Registered in England.
Registration No. 2448048
Registered Office:
St Hugh's, 23 Newport,
Lincoln LN1 3DN

J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,
Nottinghamshire, England DN22 6HG

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409
www.j-flex.co.uk

